

DONIFLON® 2030 has a superior chemical resistance to nearly all media, especially for strong alkalis. Not suitable for molten alkali metals and fluorine compounds. DONIFLON® 2030 is recommended for the pharmaceutical and food industries. It has enhanced creep performance compared to virgin PTFE materials.

PROPERTIES

		SEALABILITY PERFORMANCE	CHEMICAL RESISTANCE
SUPERIOR			
EXCELLENT			
VERY GOOD	MECHANICAL RESISTANCE		
GOOD		THERMAL RESISTANCE	
MODERATE			

APPROPRIATE INDUSTRIES & APPLICATIONS

- POTABLE WATER SUPPLY
- STEAM SUPPLY
- GAS SUPPLY
- CHEMICAL INDUSTRY
- PETROCHEMICAL INDUSTRY
- PHARMACEUTICAL INDUSTRY
- FOOD INDUSTRY
- PAPER AND CELLULOSE INDUSTRY
- REFRIGERATION AND COOLING
- COMPRESSORS AND PUMPS
- VALVES


Composition	PTFE, barium sulfate.
Colour	White
Approvals	Please inquire.

TECHNICAL DATA Typical values for a thickness of 2 mm

Density	DIN 28090-2	g/cm ³	3.0
Compressibility	ASTM F36J	%	6
Recovery	ASTM F36J	%	40
Tensile strength	ASTM F152	MPa	10
Stress resistance	DIN 52913		
30 MPa, 16 h, 150 °C		MPa	13
Specific leak rate	DIN 3535-6	mg/(s·m)	0.002
pH range			0-14
Operating conditions			
Minimum temperature		°C/°F	-200/-328
Maximum temperature		°C/°F	260/500
Pressure		bar/psi	80/1160

P-T DIAGRAM

EN 1514-1, Type IBC, PN 40, DIN 28091-2 / 3.8, 2.0 mm



- General suitability - Under common installation practices and chemical compatibility.
- Conditional suitability - Appropriate measures ensure maximum performance for joint design and gasket installation. Technical consultation is recommended.
- Limited suitability - Technical consultation is mandatory.

Dimensions of standard sheets

Sheet size (mm): 1500 x 1500
Thickness (mm): 1.5 | 2.0 | 3.0
Other dimensions and thicknesses are available on request.

Acetamide	+	Dioxane	+	Oleic acid	+
Acetic acid, 10%	+	Diphtyl (Dowtherm A)	+	Oleum (Sulfuric acid, fuming)	+
Acetic acid, 100% (Glacial)	+	Esters	+	Oxalic acid	+
Acetone	+	Ethane (gas)	+	Oxygen (gas)	+
Acetonitrile	+	Ethers	+	Palmitic acid	+
Acetylene (gas)	+	Ethyl acetate	+	Paraffin oil	+
Acid chlorides	+	Ethyl alcohol (Ethanol)	+	Pentane	+
Acrylic acid	+	Ethyl cellulose	+	Perchloroethylene	+
Acrylonitrile	+	Ethyl chloride (gas)	+	Petroleum (Crude oil)	+
Adipic acid	+	Ethylene (gas)	+	Phenol (Carbolic acid)	+
Air (gas)	+	Ethylene glycol	+	Phosphoric acid, 40%	+
Alcohols	+	Formaldehyde (Formalin)	+	Phosphoric acid, 85%	+
Aldehydes	+	Formamide	+	Phthalic acid	+
Alum	+	Formic acid, 10%	+	Potassium acetate	+
Aluminium acetate	+	Formic acid, 85%	+	Potassium bicarbonate	+
Aluminium chloride	+	Formic acid, 100%	+	Potassium carbonate	+
Aluminium chloride	+	Freon-12 (R-12)	+	Potassium chloride	+
Aluminium sulfate	+	Freon-134a (R-134a)	+	Potassium cyanide	+
Amines	+	Freon-22 (R-22)	+	Potassium dichromate	?
Ammonia (gas)	+	Fruit juices	+	Potassium hydroxide	?
Ammonium bicarbonate	+	Fuel oil	+	Potassium iodide	+
Ammonium chloride	+	Gasoline	+	Potassium nitrate	+
Ammonium hydroxide	+	Gelatin	+	Potassium permanganate	+
Amyl acetate	+	Glycerine (Glycerol)	+	Propane (gas)	+
Anhydrides	+	Glycols	+	Propylene (gas)	+
Aniline	+	Helium (gas)	+	Pyridine	+
Anisole	+	Heptane	+	Salicylic acid	+
Argon (gas)	+	Hydraulic oil (Glycol based)	+	Seawater/brine	+
Asphalt	+	Hydraulic oil (Mineral type)	+	Silicones (oil/grease)	+
Barium chloride	+	Hydraulic oil (Phosphate ester based)	+	Soaps	+
Benzaldehyde	+	Hydrazine	+	Sodium aluminate	?
Benzene	+	Hydrocarbons	+	Sodium bicarbonate	+
Benzoic acid	+	Hydrochloric acid, 10%	+	Sodium bisulfite	+
Bio-diesel	+	Hydrochloric acid, 37%	+	Sodium carbonate	+
Bio-ethanol	+	Hydrofluoric acid, 10%	-	Sodium chloride	+
Black liquor	+	Hydrofluoric acid, 48%	-	Sodium cyanide	+
Borax	+	Hydrogen (gas)	+	Sodium hydroxide	?
Boric acid	+	Iron sulfate	+	Sodium hypochlorite (Bleach)	?
Butadiene (gas)	+	Isobutane (gas)	+	Sodium silicate (Water glass)	+
Butane (gas)	+	Isooctane	+	Sodium sulfate	+
Butyl alcohol (Butanol)	+	Isoprene	+	Sodium sulfide	+
Butyric acid	+	Isopropyl alcohol (Isopropanol)	+	Starch	+
Calcium chloride	+	Kerosene	+	Steam	+
Calcium hydroxide	+	Ketones	+	Stearic acid	+
Carbon dioxide (gas)	+	Lactic acid	+	Styrene	+
Carbon monoxide (gas)	+	Lead acetate	+	Sugars	+
Cellosolve	+	Lead arsenate	+	Sulfur	+
Chlorine (gas)	+	Magnesium sulfate	+	Sulfur dioxide (gas)	+
Chlorine (in water)	+	Maleic acid	+	Sulfuric acid, 20%	+
Chlorobenzene	+	Malic acid	+	Sulfuric acid, 98%	?
Chloroform	+	Methane (gas)	+	Sulfuryl chloride	?
Chloroprene	+	Methyl alcohol (Methanol)	+	Tar	+
Chlorosilanes	+	Methyl chloride (gas)	+	Tartaric acid	+
Chromic acid	+	Methylene dichloride	+	Tetrahydrofuran (THF)	+
Citric acid	+	Methyl ethyl ketone (MEK)	+	Titanium tetrachloride	?
Copper acetate	+	N-Methyl-pyrrolidone (NMP)	+	Toluene	+
Copper sulfate	+	Milk	+	2,4-Toluenediisocyanate	+
Creosote	+	Mineral oil (ASTM no.1)	+	Transformer oil (Mineral type)	+
Cresols (Cresylic acid)	+	Motor oil	+	Trichloroethylene	+
Cyclohexane	+	Naphtha	+	Vinegar	+
Cyclohexanol	+	Nitric acid, 10%	+	Vinyl chloride (gas)	+
Cyclohexanone	+	Nitric acid, 65%	+	Vinylidene chloride	+
Decalin	+	Nitrobenzene	+	Water	+
Dextrin	+	Nitrogen (gas)	+	White spirits	+
Dibenzyl ether	+	Nitrous gases (NOx)	+	Xylenes	+
Dibutyl phthalate	+	Octane	+	Xylenol	+
Dimethylacetamide (DMA)	+	Oils (Essential)	+	Zinc sulfate	+
Dimethylformamide (DMF)	+	Oils (Vegetable)	+		

CHEMICAL RESISTANCE CHART

The recommendations made here are intended to be a guideline for the selection of the suitable gasket quality. Because the function and durability of the products depend upon a number of factors, the data may not be used to support any warranty claims.

- + Recommended
- ? Recommendation depends on operating conditions
- Not recommended



DONIT TESNIT®, d.o.o.

Cesta komandanta Staneta 38
1215 Medvode, Slovenia

Phone: +386 (0)1 582 33 00

Fax: +386 (0)1 582 32 06
+386 (0)1 582 32 08

Web: www.donit.eu

E-mail: info@donit.eu

Copyright © 2015 DONIT TESNIT, d.o.o.

All rights reserved

Date of issue: 01.06.2015 / TDS-D2030-05-2015

All information and data quoted are based upon years of experience in the production and operation of sealing elements. This data may not be used to support any warranty claims. With its publication this latest edition supersedes all previous issues and is subject to change without further notice.