



# CF205

**CHEMFAB® CF205** is a Primary-Series PTFE-coated glass cloth with excellent release and chemical resistance properties, even at elevated temperatures.

**CHEMFAB® CF205** is typically used for “non-stick” applications in the packaging and plastics industries, and also as release sheets for food and other processing industries.

| TYPICAL PROPERTIES             | UNIT             | VALUE               | TEST METHOD    |
|--------------------------------|------------------|---------------------|----------------|
| <b>Weight:</b>                 | g/m <sup>2</sup> | 250                 | FTMS 191A-5041 |
| <b>Thickness:</b>              | mm               | 0.120               | FTMS 191A-5030 |
| <b>Tensile Strength:</b>       | N/cm             | 290 x 260           | FTMS 191A-5102 |
| <b>Trap Tear Strength:</b>     | N                | 20 x 18             | FTMS 191A-5136 |
| <b>PTFE Content:</b>           | %                | 58                  | -              |
| <b>Temperature Resistance:</b> | °C               | -150 to +260        | -              |
| <b>Standard Widths:</b>        | mm               | 1000;<br>1250; 1525 | -              |

\*Formerly CF 700-5, Tygaflor 216A

Saint-Gobain Performance Plastics sales, fabrication and distribution facilities are situated at the following locations:

## Ireland

Tel. +353 65 9080170  
Fax. +353 65 9080177  
E-mail: [aff.europe@saint-gobain.com](mailto:aff.europe@saint-gobain.com)

## Germany

Tel. +49 21 54 60 190  
Fax. +49 21 54 60 194  
E-mail: [aff.germany@saint-gobain.com](mailto:aff.germany@saint-gobain.com)

## France

Tel. +33 4 68635353  
Fax. +33 4 68632646  
E-mail: [aff.france@saint-gobain.com](mailto:aff.france@saint-gobain.com)

## UK

Tel. +44 1706 746900  
Fax. +44 1706 746991  
E-mail: [aff.uk@saint-gobain.com](mailto:aff.uk@saint-gobain.com)

[www.chemfab.com](http://www.chemfab.com)

CHEMFAB® is a registered trademark.

The data listed herein fall within the normal range of product properties for the products described, but they should not be used to establish specification limits nor used alone as the basis of design. SAINT-GOBAIN assumes no obligation or liability for any advice furnished by it or for results obtained to these products. All such advice is provided gratis and Buyer assumes sole responsibility for results obtained in reliance thereon. SAINT-GOBAIN warrants that the material itself does not knowingly infringe any patent, but no license is implied nor is any further warranty made.

©2010 Saint-Gobain Performance Plastics Corporation  
KIIR-0108-036