



# CF206

**CHEMFAB® CF206** is a primary series PTFE-coated glasscloth. This material has an extra glossy and flat surface profile and is particularly suitable for applications which require the smoothness and wear properties of a highly consolidated PTFE-coating.

**CHEMFAB® CF206** is typically used as a release sheet for covering PVC welding platens on heat sealing packaging equipment, or as a covering on fabric dryer cylinders.

TYPICAL PROPERTIES	UNIT	VALUE	TEST METHOD
Weight:	g/m <sup>2</sup>	300	FTMS 191A-5041
Thickness:	mm	0.150	FTMS 191A-5030
Tensile Strength:	N/cm	310 x 260	FTMS 191A-5102
Trap Tear Strength:	N	20 x 18	FTMS 191A-5136
PTFE Content:	%	65	-
Temperature Resistance:	°C	-150 to +260	-
Standard Widths:	mm	1010, 1250, 1525	-

*\* Formerly CF 700-6 G or CF 700-6 GX (Tygaflor 216AA, 316AA) both products combined*

Saint-Gobain Performance  
Plastics sales, fabrication and  
distribution facilities are  
situated at the following  
locations:

## Ireland

Tel. +353 65 9080170

Fax. +353 65 9080177

E-mail: [aff.europe@saint-gobain.com](mailto:aff.europe@saint-gobain.com)

## Germany

Tel. +49 21 54 60 190

Fax. +49 21 54 60 194

E-mail: [aff.germany@saint-gobain.com](mailto:aff.germany@saint-gobain.com)

## France

Tel. +33 4 68635353

Fax. +33 4 68632646

E-mail: [aff.france@saint-gobain.com](mailto:aff.france@saint-gobain.com)

## UK

Tel. +44 1706 746900

Fax. +44 1706 746991

E-mail: [aff.uk@saint-gobain.com](mailto:aff.uk@saint-gobain.com)

[www.chemfab.com](http://www.chemfab.com)

CHEMFAB® is a registered trademark.

The data listed herein fall within the normal range of product properties for the products described, but they should not be used to establish specification limits nor used alone as the basis of design. SAINT-GOBAIN assumes no obligation or liability for any advice furnished by it or for results obtained to these products. All such advice is provided gratis and Buyer assumes sole responsibility for results obtained in reliance thereon. SAINT-GOBAIN warrants that the material itself does not knowingly infringe any patent, but no license is implied nor is any further warranty made.

©2010 Saint-Gobain Performance Plastics  
Corporation  
KIIR-0108-041